

Technical Data Sheet

Applications

- Auto oem
- Auto plastics
- Auto refinish
- Automotive
- Automotive parts & accessories
- Automotive protective coatings
- Cosmetic ingredients - nails

Product Description

Eastman Cellulose Acetate Butyrate (CAB-551-0.01) has many unique attributes that will serve useful across many different coating application areas. It has the lowest T_g (glass transition temperature) of the CAB portfolio. It also has the second lowest M(n), which helps its compatibility with other coatings components. It is compatible with numerous cross-linking resins and has a lower solution viscosity. In coatings, Eastman CAB-551-0.01 gives clear films, reduces surface tack and mottling, minimizes cratering, improves flow and thermal reflow, and provides inter coat adhesion and good UV stability. Its good compatibility with a wide range of curing resin systems and its solubility in a wide variety of solvents and solvent combinations make it useful as an additive in numerous coating compositions. When dissolved in appropriate solvents selected for CAB-551-0.01, a clear, colorless solution is produced. It is useful in lacquers for glass, plastic, wire and release coatings and is available in pellet form.

Eastman CAB-551-0.01 is based on cellulose, one of the most abundant natural renewable resources. The calculated approximate bio-content value of 37% for Eastman CAB-551-0.01 was determined by using six bio-based carbon atoms per anhydroglucose unit divided by the total number of carbons per anhydroglucose unit. Although the value reported is not specifically measured for bio-carbon, it can be estimated based on typical partition data.

For applications that require food contact compliance, please refer to Eastman CAB 551-0.01, Food Contact.

Typical Properties

Property	Typical Value, Units
General	
Viscosity ^a	
s	0.02
Poise	0.038
Acetyl Content	2 wt %
Butyryl Content	52 wt %
Hydroxyl Content	2 wt %
Moisture Content	3.0 max %
T _g ^b	85 °C
Specific Gravity	1.16
Char Point	260 °C
Acidity	
as Acetic Acid	0.02 wt %
Tukon Hardness	15 Knoop
Wt/Vol	
(Cast Film)	1.16 kg/L (9.67 lb/gal)

^aViscosity determined by ASTM Method D 1343. Results converted to poises (ASTM Method D 1343) using the solution density for Formula A as

stated in ASTM Method D 817 (20% Cellulose ester, 72% acetone, 8% ethyl alcohol).

^bGlass Transition Temperature

Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

12/5/2023 11:24:09 AM

© 2024 Eastman Chemical Company or its subsidiaries. All rights reserved. As used herein, ® denotes registered trademark status in the U.S. only.